



Polyflor Ltd
PO Box 3 Radcliffe New Road, Whitefield
M45 7NR MANCHESTER
United Kingdom

Your notice of
06-01-2021

Your reference

Date
15-03-2021

Analysis Report 21.00064.01

Required tests :

EN 13501-1 (2019)

Sample id	Information given by the client	Date of receipt
T2100193	Geotone Quicklay PUR	06-01-2021

Kristina De Temmerman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2100193 - Geotone Quicklay PUR

Information given by the client

Product standard	EN 13501-1 (2019)
Floor covering type	Heterogeneous polyvinyl chloride floor coverings
EN product standard	EN ISO 10582
FR treated	no
Mass	2.7 kg/m ²
Thickness	2.2 mm

Notified body No: 0493

Reference: T2100193 - Geotone Quicklay PUR

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test

Product standard EN 13501-1 (2019)

Classification of resilient floor coverings in accordance with EN 14041 (2004) § 4.1.4
“The resilient floor coverings listed in Table 3, in the end uses identified in the table, are classified without further testing (CWFT) in the classes shown and do not require testing in respect of these end uses and classes”.

Table 3 – Classes of reaction to fire for resilient floor coverings, classified without further testing

Floor covering type ¹	EN product standard	Minimum mass (kg/m ²)	Maximum mass (kg/m ²)	Minimum overall thickness (mm)	Class ² Floorings
Plain and decorative Linoleum	EN 548	2.3	4.9	2	Efl
Homogeneous and heterogeneous polyvinyl chloride floor coverings	EN 649	2,3	3,9	1,5	E _n
Polyvinyl chloride floor coverings with foam layer	EN 651	1.7	5.4	2	E _n
Polyvinyl chloride floor covering with cork-based backing	EN 652	3.4	3.7	3.2	E _n
Expanded (cushioned) polyvinyl chloride floor coverings	EN 653	1,0	2,8	1,1	E _n
Semi-flexible polyvinyl chloride tiles	EN 654	4.2	5.0	2	E _n
Linoleum on corkment backing	EN 687	2.9	5.3	2.5	E _n
Homogeneous and heterogeneous smooth rubber floor coverings with foam backing	EN 1816	3.4	4.3	4	E _n
Homogeneous and heterogeneous smooth rubber floor coverings	EN 1817	3.0	6.0	1.8	E _n
Homogeneous and heterogeneous relief rubber floor coverings	EN 12199	4.6	6.7	2.5	E _n
¹⁾ Floor covering loose laid over any wood based substrate of at least Class D-s2,d0 or any substrate of at least Class A2-s1,d0. ²⁾ Class as provided for in Table 2 in the Annex to Decision 2000/147/EC.					



Classification

Class E_{fl}



Reference: T2100193 - Geotone Quicklay PUR

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test	09-02-2021
Standard used	EN ISO 9239-1 (2010)
Product standard	EN 13501-1 (2019)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate	Particle board - density (680 ± 50) kg/m ³
Mounting	Loose-laid
Specimens have not been cleaned	

Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux * kW/m ²
	10 min	20 min	30 min		
Width					
#1	14	14	14	12 min 09 s	10.4
Length					
#1	16	16	16	12 min 09 s	10.1
#2	17	17	17	12 min 00 s	10.0
#3	17	17	17	12 min 00 s	10.0
Average					10.0

* Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2019)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B _{f1}	E _{f1}	heat flux ≥ 8,0 kW/m ²
C _{f1}	E _{f1}	heat flux ≥ 4,5 kW/m ²
D _{f1}	E _{f1}	heat flux ≥ 3,0 kW/m ²

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Width		
#1	38	182
Length		
#1	48	220
#2	38	223
#3	37	183
Average		209

Additional classification in accordance with EN 13501-1 (2019)	
smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2



Reaction to fire classification : B_n/ s1

*Loose-laid on a combustible substrate**

** End use substrates of wood and of classes A1 and A2-s1,d0 (EN 13238:2010 § 5.2.3)*

Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of performance by the manufacturer within the context of system 3 of assessment and verification of constancy of performance and CE marking under the Construction Products Regulation.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (e.g. no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”