

Exova Warringtonfire
Holmesfield Road
Warrington
WA1 2DS
United Kingdom

T : +44 (0) 1925 655 116
F : +44 (0) 1925 655 419
E : warrington@exova.com
W: www.exova.com



Testing. Advising. Assuring.

Title:

CLASSIFICATION OF
REACTION TO FIRE
PERFORMANCE
IN ACCORDANCE WITH
EN 13501-1:2007+A1: 2009.

Notified Body No:

0833

Product Name:

"Acoustix Forest FX PUR" /
"Acoustix Harmony FX PUR"
/ "SILENTFLOR"

Report No:

WF 339193

Issue No:

2

Prepared for:

Polyflor Limited, PO Box 3,
Radcliffe New Road,
Whitefield, Manchester,
M25 7NR

Date:

21th March 2014

1. Introduction

This classification report defines the classification assigned to "Acoustix Forest FX PUR" / "Acoustix Harmony FX PUR" / "SILENTFLOR", a vinyl floor product, in accordance with the procedures given in EN 13501-1:2007+A1: 2009.

2. Details of classified product

2.1 General

The product, "Acoustix Forest FX PUR" / "Acoustix Harmony FX PUR" / "SILENTFLOR", a vinyl floor product, is defined as being suitable for floorcovering applications.

2.2 Product description

The product, "Acoustix Forest FX PUR" / "Acoustix Harmony FX PUR" / "SILENTFLOR", a vinyl floor product, is fully described below and in the test reports provided in support of classification listed in Clause 3.1.

General description		Vinyl floorcovering adhered to a nominally 6mm thick fibre cement board substrate utilising "Balls F44" adhesive
Thickness of composite		9.93mm (determined by Exova Warringtonfire)
Weight per unit area of composite		13.58kg/m ² (determined by Exova Warringtonfire)
Floor covering	Product reference	"Acoustix Forest FX PUR" / "Acoustix Harmony FX PUR" / "SILENTFLOR"
	Generic type	PVC
	Name of manufacturer	Polyflor
	Colour/ pattern	Any colour / pattern
	Weight per unit area	3.00kg/m ²
	Thickness	3.7mm
	Flame retardant details	See Note 1 below
Adhesive	Product reference	"Styccobond F44"
	Generic type	Acrylic based adhesive
	Name of manufacturer	F Ball & Co. Ltd.
	Application rate	200g/m ²
	Application method	'V' notched trowel
	Flame retardant details	The manufacturer stated that no flame retardant additives were utilised in the construction of the adhesive
Substrate	Trade name	"NT D4 604"
	Generic type	Fibre cement board
	Supplier	Scheerders van de Kerkhove (SVK)
	Thickness	6mm
	Density	1800kg/m ³
Brief description of manufacturing process of the floor covering		Calendared flooring

Note 1. The sponsor of the test was unwilling to provide this information. The precise composition of the product submitted for test is regarded by the sponsor to be of a highly confidential nature and as a consequence this information is maintained by Polyflor at their Whitefield factory. This information can be inspected by Exova warringtonfire at anytime and the information is checked, stamped, signed and dated by a member of Exova warringtonfire to prevent misuse.

3. Test reports & test results in support of classification.

3.1 Test reports.

Name of Laboratory	Name of sponsor	Test reports / Classification report Nos.	Test method / extended application rules & date
Exova Warringtonfire	Polyflor Limited	WF 339166	EN ISO 11925-2
Exova Warringtonfire	Polyflor Limited	WF 339167	EN ISO 9239-1

3.2 Test results

Test method & test number		Parameter	No. tests	Results	
				Continuous parameter - mean (m)	Compliance with parameters
EN ISO 9239-1		Critical flux	3	9.0	Compliant
		Smoke		166.78	Compliant
EN ISO 11925-2	(15s exposure – surface of decorative face)	F _s	6	58.3	Compliant
	(15s exposure – edge of decorative face)	F _s	6	71.7	Compliant

4. Classification and field of application

4.1 Reference of classification

This classification has been carried out in accordance with clause 9 of EN 13501-1:2007+A1:2009.

4.2 Classification

The product, "Acoustix Forest FX PUR" / "Acoustix Harmony FX PUR" / "SILENTFLOR", a vinyl floor product, in relation to its reaction to fire behaviour is classified:

B_{FL}

The additional classification in relation to smoke production is:

s1

The format of the reaction to fire classification for floorings is:

Fire Behaviour		Smoke Production	
B_{FL}	-	s	1

i.e. **B_{FL} – s1**

Reaction to fire classification: B_{FL} – s1

4.3 Field of application

This classification is valid for the following end use applications:

- i) Floorcovering applications bonded directly to any substrate with a minimum density of 1800kg/m³, having a minimum thickness of 6mm and a fire performance of A2_{FL} or better.
- ii) Installed directly to the substrate utilising "Styccobond F44" adhesive, applied at a nominal rate of 200g/m²

This classification is also valid for the following product parameters:

Floorcovering thickness	No variation allowed
Floorcovering weight per unit area	No variation allowed
Floorcovering composition	No variation allowed
Colour/Pattern	Any variation allowed

SIGNED




.....

Matthew Dale

Certification Engineer
Technical Department

APPROVED



.....

Janet Murrell

Technical Manager
Technical Department
on behalf of **Exova Warringtonfire**

Issue 2 – 5th December 2016

This copy has been produced from a .pdf format electronic file that has been provided by Exova Warringtonfire to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without the permission of Exova Warringtonfire. The pdf. copy supplied is the sole authentic version of this document. All pdf versions of this report bear authentic signatures of the responsible Exova Warringtonfire staff.